


CLAIM AMENDMENTS:

1. (Currently amended) An aliphatic polyester resin composition contains a compound (A) of 1.0 mass part to 100 mass parts expressed by the following formula (1) as a plasticizer to an aliphatic polyester of 100 mass parts[[]]

Formula (1)



[[In]] in the formula, X denotes a trivalent polyalcohol frame; R^1 , R^2 , R^3 are selected from an acyl group having 2 to 18 carbon atoms or a hydrogen atom; the sum total of carbon numbers of R^1 , R^2 , R^3 is 10 to 22; and the average acylation rate is 50 to 90%.

2. (Original) The aliphatic polyester resin composition according to the claim 1, wherein R^1 , R^2 , R^3 of the formula (1) contain at least one acyl group having a carbon number of 8 to 18.

3. (Previously presented) The aliphatic polyester resin composition according to the claim 1, wherein the aliphatic polyester resin is a lactic acid system polyester.

4. (Currently amended) Sheets, films, or ~~other~~ products molded from the aliphatic polyester resin composition described in claim 1.